



## TEST REPORT

**CLIENT:** Universal Bedlegs  
625 Du Bois St.  
Ste A  
San Rafael, CA  
United States 94901  
  
Attn: David Cline

**Test Report No:** 654:017113-1

**Date:** January 22, 2009

**SUBJECT:** Load test.

**REFERENCE:** Letter

**SAMPLE ID:** Bed leg samples, identified by client as "**Pebble-Virgin and Recycled-Black,**" were received on 11/19/08 in good condition.

**PROCEDURE:** The samples were evaluated for load test

**RESULTS:** See test data and results on the following page.

**TEST DATE:** 1/14/09 – 1/16/09

**CERTIFICATION:** The tests reported here were conducted under the continuous direct supervision of SGS U.S. Testing Company Inc., Tulsa, OK.

**SIGNED FOR AND ON BEHALF OF  
SGS U.S. TESTING COMPANY INC.**

Robert Ross  
Materials Department Technician

S. Scott Parkhurst  
Materials Department Manager

Page 1 of 3

This report is issued by SGS U.S. Testing Company Inc. under its General Conditions for Testing Services, as printed on reverse side. SGS U.S. Testing's responsibility under this report is limited to proven negligence and will in no case be more than the amount of the testing fees. Except by special arrangement, samples are not retained by SGS U.S. Testing for more than 30 days. The results shown on this test report refer only to the sample(s) tested unless otherwise stated, under the conditions agreed upon. Anyone relying on this report should understand all of the details of the engagement. Neither the name, seals, marks nor insignia of SGS U.S. Testing may be used in any advertising or promotional materials without the prior written approval of SGS U.S. Testing. The test report cannot be reproduced, except in full, without prior written permission of SGS U.S. Testing Company Inc.

SGS U.S. Testing Company Inc. Consumer Services Division 1325 North 108th East Avenue, Tulsa, OK 74116 t (918) 437-8333 f (918) 437-8487 www.sgs.com

## Test Procedure and Results

### LOAD TEST

Sample ID: Pebble-Virgin

Load Direction: (Vertical) Axial Compression		
Specimen	Length in.	Ultimate Load, lbs
1	3.2500	7123
2	3.2500	7415
3	3.2500	7123
4	3.2500	7196
5	3.2500	7189
Average		7209

Sample ID: Pebble-Virgin and Recycled-Black

Load Direction: (Vertical) Axial Compression		
Specimen	Length in.	Ultimate Load, lbs
1	10.0	5533
2	10.0	5338
3	10.0	5465
4	10.0	5780
5	10.0	5827
Average		5587





**Sample ID: Recycled-Black**

Load Direction: (Vertical) Axial Compression		
Specimen	Length in.	Ultimate Load, lbs
1	3.2500	5323
2	3.2500	5400
3	3.2500	5480
4	3.2500	5512
5	3.2500	5305
Average		5404

**Sample ID: Recycled-Black**

Load Direction: (Vertical) Axial Compression		
Specimen	Length in.	Ultimate Load, lbs
1	10.0	4588
2	10.0	4708
3	10.0	4661
4	10.0	4700
5	10.0	4609
Average		4653



\*\*\*\*\*

**End of Report**